

Our Ref: SW/MG/GL

4 August 2015

**Report 258866**

**Page 1 of 2**

Kvadrat A/S  
Lundbergsvej 10  
DK 8400  
Ebeltoft  
Denmark

Contact: Sharon Daniel

---

DATE RECEIVED	: 30 JUL 2015
QUALITY/REFERENCE	: Forest Nap
REPUTED FIBRE CONTENT	: 95% WOOL, 5% NYLON
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: RUST
ORDER NUMBER	: 290715
PERFORMANCE STANDARD	: GENERAL

---

REQUEST: Seam slippage, pilling and martindale abrasion

---



**S. WISEMAN**  
**LABORATORY DIRECTOR**



**M. GRAINGER**  
**SENIOR TECHNOLOGIST**

*This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.*



118 Lupton Avenue Leeds LS9 6ED  
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 Email: hstts@hstts.co.uk  
Registered No. 2899980 VAT No. 613 4310 86



**Report 258866**

**PHYSICAL**

**BS EN ISO 13936-2:2004 SEAM SLIPPAGE**

	Length	Width
Seam opening at 180 N	3.5 mm	3.3 mm

**BS EN ISO 12945-2:2000 PILLING MODIFIED MARTINDALE**

Revs	Grade
500	4
1000	4
2000	4
5000	4

Sample tested: As Received

Sample tested against Wool abradant as specified in BS EN ISO 12947.

**BS EN ISO 12947:1998 ABRASION**

12 kPa Load

Number of rubs to breakdown:	53,750
------------------------------	--------

